



# Krytox™ NRT 8908

## Performance Lubricants

## Product Information

Krytox™ NRT 8908\* is a special high-pressure oxygen, white, creamy lubricant for reactive gas service. It has excellent lubrication over a broad temperature range. Krytox™ NRT 8908 is nonflammable and chemically inert. Krytox™ allows extended lubrication intervals and longer equipment life. This product has been formulated with special oils and thickeners for use in applications with high-pressure oxygen and other reactive gases.

Krytox™ NRT 8908 has been tested by BAM with the following results:

- Ignition sensitivity to gaseous impacts: 340 bar at 60 °C (140 °F) and 210 bar up to 200 °C (392 °F)
- Autogenous ignition temperature: >500 °C (932 °F) at 263 bar
- Reactivity in liquid oxygen on mechanical impact: Compatible, no reaction at 750 Nm (the test limit)

\*NSF 15672 registered

Property	Krytox™ NRT 8908
Standard NLGI Grade	2
Thickener	Inorganic
Estimated Useful Temperature Range, °C (°F)	-40 to 180 (-40 to 356)
Pour Point, °C (°F)	-54 (-65)
Base Oil Viscosity, cSt	
20 °C (68 °F)	140
40 °C (104 °F)	49
100 °C (212 °F)	7
Vapor Pressure at 20 °C (68 °F) (Knudsen)	≤5 x 10 <sup>-6</sup>
Appearance	Light gray, creamy paste
Specific Gravity	2.0
Volatility of Base Oil, wt% loss in 22 hr at 121 °C (250 °F)	1.3
Food Contact Approval	NSF H-1

These values are typical properties and not specifications.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For product information, industry applications, technical assistance, or global distributor contacts, visit [krytox.com](http://krytox.com) or within the U.S. and Canada, call 1-844-773-CHEM/2436 or outside of the U.S., call 1-302-773-1000.

© 2017 The Chemours Company FC, LLC. Krytox™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Replaces: K-08989-2

C-11474 (12/17)

